



LEXAN® FR 700–701 FILM

Product Data Sheet

DESCRIPTION

LEXAN® FR 700–701 is an opaque **black**, flame retardant polycarbonate film. With a UL 94V-0 listing at $\geq .010$ ", this film meets stringent requirements for a wide range of electrical and electronic applications.

UL File Number: E61257(R).

Potential applications include:

- power supply insulation
- disc drive insulation
- bus bar insulation
- keyboard insulation
- TV/monitor insulation
- PC board insulation
- business equipment insulation
- foil laminated for insulation and shielding

CONFIGURATION

Finish: Velvet/fine matte

Standard Roll Width: 48"

Minimum Gauge: .010"

Standard Gauges: .010", .017"

Custom Gauges: .011" – .030"

TYPICAL PROPERTY VALUES*

Property	Test Method	Units	FR 700 Value
PHYSICAL			
Specific Gravity	ASTM D792	—	1.32
Area Factor	Calculation	ft ² /lb/mil m ² /lb/mil	145.75 13.54
Water Absorption, Equilibrium, 24 Hrs	ASTM D570	%	0.28
MECHANICAL			
Tensile Strength	ASTM D882	psi	
@ Yield			9,500
Ultimate			8,800
Tensile Modulus	ASTM D882	psi	310,000
Elongation	ASTM D882	%	25–50
Tear Strength			
Initiation	ASTM D1004	g/mil	770–910
Propagation	ASTM D1922	g/mil	16–40
Puncture Resistance	ASTM D1048	lb/in	332
THERMAL			
Tensile Heat Distortion @ 50 psi	ASTM D1637	°C	150
Heat Deflection Temperature @ 264 psi	ASTM D648	°C	135
Thermal Conductivity	ASTM C177	Watt/M-°C	0.19
Glass Transition	DSC	°C	156

®Registered Trademark of GE

(continued on reverse)

*These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local GE Plastics Structured Products representative or the GE Plastics Structured Products Quality Services Department.

LEXAN

AGENCY SUMMARY

LEXAN FR 700–701 film has been tested under a number of agency testing protocols including UL 746A and UL 746B, IEC Publication 85 and CSA C22.2 Class 9052 30. The tables to the right summarize our UL and CSA listings for LEXAN FR 700–701.

In addition to the significant breadth of CSA and UL listings that LEXAN FR 700–701 has received, GE Plastics is proud to state that our facility has been registered by The British Standards Institute to the International Organization for Standardization, ISO 9002 Standards for Quality.

For more information call: (800) 451-3147 or (413) 448-5400.

Although all information, recommendations, or advice contained herein is given in good faith, no guarantee is made that the same results as those described will be obtained or, as to the effectiveness or safety of any design, and General Electric Company*, USA, its subsidiaries, affiliates and authorized representatives shall in no event be held responsible for any loss incurred through such use of the products. Each user shall make its own determination of the suitability of the products or any such information, recommendations or advice for its own particular use. The products of General Electric Company, its subsidiaries or affiliates are sold in any event subject to the Conditions of Sale constituting part of the applicable representative or other sales agreement or printed on the back of order acknowledgments or invoices or are available upon request. Nothing in this or any other document or any oral recommendation or advice shall be deemed to alter, vary, supersede, or waive any of the Conditions of Sale. Statements concerning possible or suggested uses of the materials or designs described herein are not to be construed as constituting a license under any General Electric Company or subsidiary or affiliate company patent covering such use or as recommendations for use of such materials or designs in the infringement of any patent.

TYPICAL PROPERTY VALUES (continued)

Property	Test Method	Units	FR 700 Value
ELECTRICAL			
Dielectric Strength (@ 10 mils)	ASTM D149	Volts	17,000
Dielectric Constant @ 25°C, 50% RH	ASTM D150	—	—
@ 60 Hz			2.9
@ 1,000 Hz			2.8
@ 1,000,000 Hz			2.8
Dissipation Factor @ 25°C, 50% RH	ASTM D150	—	—
@ 60 Hz			0.0026
@ 1,000 Hz			0.0028
@ 1,000,000 Hz			0.0117
Volume Resistivity @ 25°C, 50% RH	ASTM D257	ohm-cm	10 ¹⁶
Surface Resistivity @ 25°C, 50% RH	ASTM D257	Ω/□	10 ¹⁵
FLAMMABILITY			
UL Flammability*	UL Bulletin 94	—	V-0 ≥ .010"
Oxygen Index	ASTM D2863	—	33
Flash Point		—	825°F(440°C)
Self-Ignition Temperature		—	1120°F(605°C)
FMVSS 302	ASTM D618	—	All Pass
NFPA 258–NBS	ASTM E662	—	D(4) = 6
Smoke Chamber Test (10 mil)		—	D(max) = 36

*This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

UL LISTING SUMMARY

File #E61257(R)

Material	Color	Thickness		UL-94 Flame Rating*	Relative Thermal Index			Performance Level Categories (PLCs)				
		mils	mm		Elect.	Mechanical		H W I	H A I	H V T R	D 4 9 5	C T I
						With Elong.	Without Elong. (Tensile)					
LEXAN FR-700 (FR7+)	bk	10–14	.25–.35	V-0	130	125	130	1	0	—	—	3
	bk	15–29	.38–.74	V-0	130	125	130	0	0	—	—	3
	bk	≥30	≥.76	V-0	130	125	130	0	0	—	—	3

*This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

CSA LISTING SUMMARY

File #LR84942

Material Type	Minimum Thickness		Temp. Class	Requirements in Standard								
	mm	inches		CSA C22.2 No.						IEC No.		
				1-M1990	6-M1984	66-1988	223-1987	234	950	65	950	
LEXAN FR-700	.25	.010	130°C	A	A	A	A	A	A	A	A	A

Note: "A" indicates compliance with all of the requirements of the indicated agency standard.



GE Structured Products

General Electric Company
One Plastics Avenue
Pittsfield, MA 01201

www.structuredproducts.ge.com

® Registered Trademark of General Electric Company

* Not connected with the English company of similar name.