



## GE Structured Products

### LEXAN® 9600 Sheet

#### Product Data Sheet

#### INDUSTRIAL

#### DESCRIPTION

LEXAN® 9600 sheet offers improved flammability characteristics than conventional LEXAN polycarbonate sheet. It is formulated to meet the standards of UL Bulletin, Class I. (Certain colors are limited to Class II use.) Developed to meet industry flammability codes, LEXAN 9600 sheet is widely used in power tools, electrical appliances, communications equipment, business machines, safety equipment and aircraft components.

The improved flammability and slightly higher (5 to 10 degrees) heat deflection temperature of LEXAN 9600 sheet are accompanied by essentially the same physical, electrical, chemical and fabricating properties exhibited by standard LEXAN sheet.

#### TYPICAL PROPERTY VALUES\*

Property	Test Method	Units	Value
<b>PHYSICAL</b>			
Specific Gravity	ASTM D792	—	1.25
Water Absorption, Equilibrium, 24 Hrs	ASTM D570	%	0.20
Light Transmission (avg.), .125" thickness	ASTM D1003	%	85
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	psi	9,500
@ Yield			9,000
Ultimate			95
Elongation	ASTM D638	%	235,000
Tensile Modulus	ASTM D638	psi	13,500
Flexural Strength	ASTM D790	psi	370,000
Flexural Modulus	ASTM D790	psi	12,500
Compressive Strength	ASTM D695	psi	50
Dynatup Impact Strength, 1/2" dia. dart, (gauge dependant)***, @ 73°F	ASTM D3783	ft-lbs	>320
Gardner Impact Strength, round tip (gauge dependant)***, @ 73°F	ASTM D3029	in-lbs	
Izod Impact Strength, (gauge dependant)***	ASTM D256A	ft-lbs/in	
Notched @ 73°F			2.4
Unnotched @ 73°F			NB
<b>THERMAL</b>			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75 x 10 <sup>-5</sup>
Heat Deflection Temperature	ASTM D648	°F	280
@ 264 psi			
<b>FLAMMABILITY</b>			
UL Flammability**	UL 94	—	V-0 (90 mils and above) V-2 (34–89 mils)
FAA Flammability @ 40 to 125 mils	FAR 25.853	—	Passes A&B
ATS 1000 @ 40 to 125 mils	—	—	Pass

\*\*This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

\*\*\*Reported values based on .125" gauge thickness.

®Registered Trademark of General Electric Company

\*These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local GE Structured Products representative or the GE Structured Products Quality Services Department.

Although all information, recommendations, or advice contained herein is given in good faith, no guarantee is made that the same results as those described will be obtained or, as to the effectiveness or safety of any design, and General Electric Company\*, USA, its subsidiaries, affiliates and authorized representatives shall in no event be held responsible for any loss incurred through such use of the products. Each user shall make its own determination of the suitability of the products or any such information, recommendations or advice for its own particular use. The products of General Electric Company, its subsidiaries or affiliates are sold in any event subject to the Conditions of Sale constituting part of the applicable representative or other sales agreement or printed on the back of order acknowledgments or invoices or are available upon request. Nothing in this or any other document or any oral recommendation or advice shall be deemed to alter, vary, supersede, or waive any of the Conditions of Sale. Statements concerning possible or suggested uses of the materials or designs described herein are not to be construed as constituting a license under any General Electric Company or subsidiary or affiliate company patent covering such use or as recommendations for use of such materials or designs in the infringement of any patent.

LEXAN  
GE



For more information call: (800) 451-3147.

### GE Structured Products

General Electric Company  
One Plastics Avenue  
Pittsfield, MA 01201

[www.structuredproducts.ge.com](http://www.structuredproducts.ge.com)

® Registered Trademark of General Electric Company

\* Not connected with the English company of similar name.

SPD-4302C (4/98) LMC